



PRODUCT DATA SHEET

Edition 12.2017/v1
CSC Master Format™ 09 67 00
FLUID-APPLIED FLOORING

Sikafloor® Extender T

THICKENING AGENT FOR EPOXY RESIN SYSTEMS

Description	Sikafloor® Extender T is an inert, fine, white, fibrous polymer powder used as a thickening agent for Sikafloor® epoxy systems.
Where to Use	<ul style="list-style-type: none"> In combination with: Sikafloor®-156^{CA}, Sikafloor®-261^{CA}, Sikagard®-381, Sikafloor® Fastflor® CR, Sikagard®-62^{CA} and other Sika® epoxy systems. For applications on horizontal surfaces to create custom orange peel textures. For applications on vertical surface to hold the resin in place during cure. To create a thin set, fine texture, crack filler and patching gel.

Advantages	<ul style="list-style-type: none"> Allows for viscosity adjustment during Sikafloor® resin applications to suit site conditions. Economical, easy to mix and use. No effect on pot life or cure rate. Low addition rate to change viscosity when compared to other epoxy thickening agents. Non-carcinogenic. Inert non-reactive filler.
-------------------	--

Technical Data	
Packaging	1 kg (2.2 lb) packaged in a 20 L (5 US gal.) plastic pail. Note: Sika® measuring cup enclosed in each pail / each cup holds approx 18 g (0.63 oz) Approx. 55 Sika® measuring cups are weighed-out from each 1 kg (2.2 lb) pail.
Shelf Life	3 years in original unopened packaging. Store dry between 10 and 25 °C (50 and 77 °F). Protect from moisture.

Addition Rate Guidelines	The precise addition rate of Sikafloor® Extender T for a given installation can only be calculated on site. The suitability of a Sika® resin for a given application is dependant on the interaction of many different factors, some of which are not consistent. Example: slope of substrate - substrate roughness - material, substrate and ambient air temperature - layer thickness - viscosity of the mixed resins - quantity and size of broadcast sand - setting properties of the resin. In practise, the applicator must make a trial mix that achieves the viscosity he requires by feel. He can then make minor adjustments to improve workability in subsequent mixes or as site conditions change.
---------------------------------	---

The following Sikafloor® Extender T addition rate chart by product and application is a guideline only. All recommendations are based on testing completed in a controlled environment of 20 °C (68 °F). In general, colder application temperatures require a lower addition rate and warmer conditions require more to achieve the same workability.

Recommendations are provided based on the number of Sika® measuring cups required. Fill Sika® cup, lightly tap to settle powder, then refill and strike off flush. Using this fill method, the Sika® measuring cup will weigh-out approx. 18 g (0.63 oz) of Sikafloor® Extender T.

Addition Rate Chart	Product Name	Smooth Wall Coating	Orange Peel Texture	Crack Filler Gel
	Sikafloor®-156 ^{CA}	8 Sika® cups per 10 L (2.64 US gal.) unit	N/A	N/A
	Sikafloor®-261 ^{CA}	3.5 Sika® cups per 10 L (2.64 US gal.) unit	14 Sika® cups per 10 L (2.64 US gal.) unit	30 Sika® cups per 10 L (2.64 US gal.) unit
	Sikagard®-381	4 Sika® cups per 10 L (2.64 US gal.) unit	15.5 Sika® cups per 10 L (2.64 US gal.) unit	30 Sika® cups per 10 L (2.64 US gal.) unit
	Sikafloor® Fastflor® CR	4 Sika® cups per 11 L (2.9 US gal.) unit	14 Sika® cups per 11 L (2.9 US gal.) unit	30 Sika® cups per 11 L (2.9 US gal.) unit
	Sikagard®-62 ^{CA}	N/A	12 Sika® cups per 10 L (2.64 US gal.) unit	25 Sika® cups per 10 L (2.64 US gal.) unit

NOTE: Lesser amounts yield a more liquid consistency, whereas greater amounts yield thicker pastes. Care must be taken on high addition rates to not dry the mixture to the point were it will not fully wet out the substrate or adhesion characteristics will be compromised. Orange Peel Textures and Crack Filler Gel addition rates must be primed with neat resin. For more information contact your local Sika Technical Sales Representative.

HOW TO USE**Mixing**

Mix Sika® resin components A + B following individual mixing instructions published on the Product Data Sheet or label. Add Sikafloor® Extender T (powder) pouring slowly over a period of 15 seconds to avoid lumps in the final mixture. Mechanically blend for two (2) more minutes, during the operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once (components A+B+Extender T) to ensure complete mixing.

Limitations

- Do not hand mix Sikafloor® Extender T/ mechanical mix only.
- Gloss maybe affected at high addition rates.
- Adhesion characteristics maybe affected at high addition rates.
- Sikafloor® Extender T maybe visible in some clear resins at high addition rates.
- Protect from contact with moisture, Sikafloor® Extender T must be kept dry.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

KEEP OUT OF REACH OF CHILDREN
FOR INDUSTRIAL USE ONLY

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SIKA CANADA INC.**Head Office**

601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9

Other locations

Toronto
Edmonton
Vancouver

1-800-933-SIKA**www.sika.ca**

Certified ISO 9001 (CERT-0102780)
Certified ISO 14001 (CERT-0102791)